
PERFECT COVER® VAPOR-PERMEABLE

DESCRIPTION:



Application: The substrate must remain dry, clean, dust-free, and free from chemical agents. It is advisable to conduct preliminary tests. Lay the rolls with an overlap of approximately 10 cm and press firmly. Processing temperature should be between 5 degrees Celsius and 40 degrees Celsius. Not suitable for recently laid concrete. The underfloor heating must be switched off.

APPLICATION

- Hardwood floor
- LVT
- Tile
- Countertops
- Stairs
- Other surfaces

FEATURES

- Self-adhesive
- Vapor-permeable
- Shock-absorbing
- Moisture resistant
- Reusable
- Anti-slip



TECHNICAL DATA

Appearance	TL.014	-
Width	TL.013	100 cm
Weight	TS EN 29073-1	160 g/m ²
Thickness	TS EN 29073-2	1,5 mm
Tensile strength (CD)	TS EN 29073-3	N/5cm 100
Tensile elongation (CD)	TS EN 29073-3	100% (+/- 10%)
Tensile strength (MD)	TS EN 29073-3	N/5cm 100
Tensile elongation (MD)	TS EN 29073-3	80% (+/-20%)
Water vapour permeability	ASTM E398	70g/m ² /24h
Tearing strength (CD)	TS EN ISO 90732-4	1 kg
Tearing strength (MD)	TS EN ISO 90732-4	2 kg
Peeling at 180	D41 1015	-

MATERIAL

- Material Non-woven made of 100% PES fibers
- Adhesive Water-based acrylic
- Color Blue
- Laminated Laminated with an impermeable, breathable nonwoven



